

Industrial Magnum

Lightweight Slabs / Porcelain Concrete



Floor: DMAG 23 Natural

6 Colours / **2** Finishes / **7** Sizes / **3** Mosaics

Industrial Magnum is a modern-industrial concrete-effect porcelain slab range in soft neutral grey tones. Subtle surface texture and detail replicate the authentic look of concrete. Magnum slabs are light, versatile, strong and scratch-resistant.



Wall: DMAG 21 Natural
Floor: DMAG 25 Natural



DMAG 21



DMAG 23



DMAG 22



DMAG 24




DMAG 25




DMAG 26

Sizes



	Size (mm)	Thickness	Finish	Colour Availability
1	3197 x 1597 (R)	6	Natural	All colours
2	2797 x 1197 (R)	6	Natural	All colours
3	2397 x 1197 (R)	6	Natural Natural Grip	All colours
4	1597 x 1597 (R)	6	Natural	All colours
5	1197 x 1197 (R)	6	Natural Natural Grip	All colours
6	1197 x 597 (R)	6	Natural	All colours
7	797 x 797 (R)	6	Natural	All colours

(R) Rectified size - square edge with bevel. Mosaics shown on next page.
Swatch colours may vary from original. Samples should be requested.




V2 - Moderate
Shade Variation

DOMUS



Wall: DMAG 21 Natural
 Floor: DMAG 25 Natural

Mosaics



	Size (mm)	Thickness	Finish	Colour Availability
1	Mosaic 75 x 75 on 297 x 297 sheet (R)	6	Natural	All colours
2	Muretto 150 x 75 on 297 x 297 sheet (R)	6	Natural	All colours
3	Mosaic 30 x 15 on 297 x 297 sheet (R)	6	Natural	All colours

(R) Rectified size – square edge with bevel.
 Swatch colours may vary from original. Samples should be requested.



Industrial Magnum

Technical Data

Product Type: Unglazed Porcelain (BS EN 14411 – Group Bla)

Use: Floors & Walls

Product Code: DMAG

DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Length & width	BS EN ISO 10545-2	± 0.60% (max. ± 2.0mm)	± 0.15%
Thickness	BS EN ISO 10545-2	± 5% (max. ± 0.5mm)	± 5%
Edge straightness	BS EN ISO 10545-2	± 0.50% (max. ± 1.5mm)	± 0.1%
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	± 0.2%
Planarity (flatness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	± 0.2%
Appearance	BS EN ISO 10545-2	> 95%	Conforms

SLIP RESISTANCE

Technical Characteristics	Industry Standards	Requirement	Finish
Areas with footwear	BS EN ISO 10545-17 (DIN 51130)	R9 from 3° to 10° R10 from 10° to 19°	Natural Natural Grip
Areas with bare feet	DIN 51097	B over 18° to 24°	Natural Grip
Slip resistance Coefficient of friction	BS 7976-2 BS EN 16165	Test results upon request	

PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	0.08% (Average value)
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm ²	52 N/mm ² (Average value)
Breaking strength	BS EN ISO 10545-4	≥ 700 N	1350 N (Average value)
Resistance to deep abrasion (unglazed tiles)	BS EN ISO 10545-6	≤ 175 mm ³	140 mm ³ (Average value)
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	ULA
High concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	UHA
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	UB min.	UA
Stain resistance	BS EN ISO 10545-14	Declared value	Class 4
Reaction to fire	Based on the decision 96/603/EC and its changes	A1 _{FL} /A1	A1 _{FL} /A1
Recycled content			DMAG 21 – 0% DMAG 23, – 16% DMAG 22, 24, 25 & 26 – 20.5%

All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale. March 2023



DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com