

Yubi

Porcelain Design



DCQP 02 Mosaic Glazed

6 Colours / 1 Finish / 1 Mosaic

Yubi is a range of finger-like mosaics, blending a contemporary format with retro glazing techniques in seven carefully considered colours. Held in stock for immediate supply—recommended for use on internal walls only.



Wall: DCQP 04 Mosaic Glazed



DCOP 05 Mosaic Glazed



DCOP 01 Mosaic Glazed

Mosaics



DCOP 01 Mosaic



DCOP 03 Mosaic



DCOP 02 Mosaic



DCOP 04 Mosaic



DCOP 05 Mosaic



DCOP 06 Mosaic

1

	Size (mm)	Thickness	Finish	Colour Availability
1	Mosaic 145 x 15 on 306 x 294 sheet (N)	7	Glazed	All colours

(N) Nominal size - pressed edge. Swatch colours may vary from original. Samples should be requested. Recommended for use on internal walls only.

V1 Low - V2 Moderate
Shade Variation

Yubi

Technical Data

Product Type: Glazed Porcelain Mosaic (BS EN 14411 – Group BIa)

Use: Walls

Product Code: DCOP

DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement (for nominal size <i>N</i>)		Actual Value
		70mm ≤ N < 150mm	N ≥ 150mm	
Length & width	BS EN ISO 10545-2	± 0.9mm	± 0.60% (max. ±2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 0.5mm	± 5% (max. ±0.5mm)	Conforms

PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	Conforms
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm ²	Conforms
Breaking strength	BS EN ISO 10545-4	< 7.5mm ≥ 700 N	Conforms
Resistance to surface abrasion	BS EN ISO 10545-7	PEI	Class 4
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Crazing resistance	BS EN ISO 10545-11	No visible signs	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GLA
High concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GHA
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	GB min.	GA
Stain resistance	BS EN ISO 10545-14	Min. Class 3	Class 5
Reaction to fire	Based on the decision 96/603/EC and its changes	A1	A1
Recycled content			0%



All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale.
March 2021

DOMUS

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com