

# Les Bijoux

*Porcelain Marble*



Floor: DRBX 03 Glossy

**5 Colours / 2 Finishes / 3 Sizes / 2 Mosaics**

The artistic allure of jewel-like surfaces with exceptional style and great expressive strength—Les Bijoux is inspired by extremely rare and precious marbles that can be compared to true works of art. Refer to Les Bijoux Magnum for 6mm-thick lightweight slab options.



Floor: DRBX 05 Glossy






Floor: DRBX 02 Glossy



Floor: DRBX 01 Glossy




DRBX 03




DRBX 02



DRBX 01




DRBX 04




DRBX 05

# Sizes




	Size (mm)	Thickness	Finish	Colour Availability
1	1797 x 797 (R)	9	Matt Glossy	All colours All colours
2	1197 x 597 (R)	9	Matt Glossy	All colours All colours
3	597 x 597 (R)	9	Matt Glossy	All colours All colours

(R) Rectified size - square edge with bevel. Mosaics shown on next page.  
Swatch colours may vary from original. Samples should be requested.






Mosaic



DRBX 01




DRBX 02



DRBX 03



DRBX 04




DRBX 05



Floor: DRBX 02 Glossy

# Mosaics & Special Pieces



	Size (mm)	Thickness	Finish	Colour Availability
1	Mosaic 147 x 27 on 297 x 297 sheet	9	Matt Glossy	All colours All colours
2	3D Mosaic 27 x 27 on 297 x 297 sheet	9	Mix*	All colours
	Plinth Skirting 597 x 46 (R)	9	Matt Glossy	All colours All colours
	Bullnose Step Tread 1197 x 330 x 30 (R)	9	Matt Glossy	All colours All colours

(R) Rectified size - square edge with bevel. \*Mix finish is a mix of Matt & Glossy finishes. Swatch colours may vary from original. Samples should be requested.



**DOMUS**

# Les Bijoux

## Technical Data

**Product Type: Glazed Porcelain (BS EN 14411 – Group BIa)**

**Use: Floors & Walls**

**Product Code: DRBX**

### DIMENSION & SURFACE QUALITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Length & width	BS EN ISO 10545-2	± 0.60% (max. ± 2.0mm)	Conforms
Thickness	BS EN ISO 10545-2	± 5% (max. ± 0.5mm)	Conforms
Edge straightness	BS EN ISO 10545-2	± 0.50% (max. ± 1.5mm)	Conforms
Orthogonality (squareness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Planarity (flatness)	BS EN ISO 10545-2	± 0.50% (max. ± 2.0mm)	Conforms
Appearance	BS EN ISO 10545-2	> 95%	Conforms

### SLIP RESISTANCE

Technical Characteristics	Industry Standards	Requirement
Slip resistance	BS 7976-2	Test results upon request
Coefficient of friction	BS EN 16165	

### PRODUCT QUALITY & DURABILITY

Technical Characteristics	Industry Standards	Requirement	Actual Value
Water absorption	BS EN ISO 10545-3	≤ 0.5%	0.08% (average value)
Modulus of rupture (bending strength)	BS EN ISO 10545-4	≥ 35 N/mm <sup>2</sup>	50 N/mm <sup>2</sup> (average value)
Breaking strength	BS EN ISO 10545-4	≥ 1300 N	3200 N (average value)
Resistance to surface abrasion (of glazed tiles)	BS EN ISO 10545-7	PEI *see classifications below	Class 5 - DRBX 03 Class 4 - DRBX 01 & 02 Class 2 - DRBX 04 Class 1 - DRBX 05
Thermal shock resistance	BS EN ISO 10545-9	No visible defects	Resistant
Crazing resistance	BS EN ISO 10545-11	No visible signs	Resistant
Frost resistance	BS EN ISO 10545-12	No surface alteration	Resistant
Chemical resistance: Low concentrations of acids & alkalis	BS EN ISO 10545-13	No visible defects	GLA - Matt GLB - Glossy
Domestic chemicals & additives for swimming pools	BS EN ISO 10545-13	GB min.	GA
Stain resistance	BS EN ISO 10545-14	Min. Class 3	Class 4 - Glossy Class 4-5 - Matt
Reaction to fire	Based on the decision 96/603/CE and its changes	A1 <sub>FL</sub> /A1	A1 <sub>FL</sub> /A1
Recycled content			20.5%

**\*PEI classifications**  
 PEI 1 - Very light traffic  
 PEI 2 - Light traffic  
 PEI 3 - Light to moderate traffic  
 PEI 4 - Moderate to heavy traffic  
 PEI 5 - Heavy to extra heavy traffic

All test results are based upon current test data provided by the manufacturer and are provided in good faith. Domus Group cannot be held responsible for any variation in the test data due to changes in manufacture or material characteristics. Errors & omissions excepted. Please refer to Domus Group Terms & Conditions of Sale. March 2023



**DOMUS**

service@domusgroup.com | t: 020 8481 9500 | domusgroup.com